



Flextech Engineering Inc.
www.flextechseals.com

Product Description

Silicone Coated Fiberglass has excellent weatherability characteristics, with excellent resistance to ozone and ultra-violet light. The silicone coating greatly reduces the porosity of the textile, allowing for greater sealing efficiency.



S17GY Data Sheet

Silicone coated fiberglass

Physical Characteristics

<u>Fiber Content</u>	<u>Fiberglass</u>
<u>Coating/Finish</u>	<u>Silicone</u>
<u>Color</u>	<u>Grey</u>
<u>Weight</u>	<u>17 oz/sq yd</u>
<u>Thickness</u>	<u>.017"</u>
<u>Weave</u>	<u>Satin</u>
<u>Flexibility</u>	<u>Excellent</u>
<u>Electrical</u>	<u>Non-conductive</u>
<u>Chemical</u>	<u>Non-reactive</u>

Temperature Parameters

<u>Silicone Service Temp</u>	<u>500 °F</u>
<u>Fabric Maximum Temp</u>	<u>1200 °F</u>
<u>Fiberglass Service Temp</u>	<u>1000 °F</u>
<u>Fiberglass Melt Temp</u>	<u>1200 °F</u>

Performance Characteristics

<u>Break Strength (warp)</u>	<u>350 lbs</u>
<u>Break Strength (fill)</u>	<u>350 lbs</u>
<u>Tear Strength (warp)</u>	<u>40 lbs</u>
<u>Tear Strength (fill)</u>	<u>40 lbs</u>
<u>Flame Resistance</u>	<u>Self-extinguishing</u>
<u>Afterglow</u>	<u>1 seconds max</u>

S17GY is specifically designed for the fabrication of removable insulation blankets for valves, flanges, expansion joints, equipment and turbines.